

ZYCRETE PMC-120

Polymer-Modified Cement for Minor Concrete Imperfections

Description: Three-component floor coating system (base, curing agent and aggregate) designed for applications where extreme moisture-mitigation is required and where the concrete exhibits minor imperfections up to 1/16" in depth. Easy-to-use, self-priming, solvent-free low-odor application.

Areas of Usage: Designed to be used as a primer, midcoat, topcoat or seal coat for pigmented broadcast systems. Excellent for use in garages, basements, commercial kitchens, mechanical rooms, chemical processing plants, food and beverage facilities, coolers, pharmaceutical plants, waste water treatment plants, wash bays. **Not recommended for exterior use (although may be used in garages).** Meets FDA, USDA, and CFIA standards.

Features / Advantages:	Moisture mitigating	Solvent free
	Extreme thermal stability	Reduced installation duration
	Superior impact resistance	Seamless, medium-build coat
	Self-priming	Low odor
	Zero VOCs	Easy application

Surface Preparation: Test for moisture and remove dust, laitance, grease, curing compounds, preparation bond-inhibiting impregnations, waxes and other contaminants. Prepare concrete via mechanical abrasion (e.g., diamond grinding) and follow with application of ZYCrete PMC-120.

Technical Data: *Note: Data / results may differ due to statistical variations, mixing methods and equipment, temperature, application methods, actual site conditions and curing conditions*

Packaging: Part A (Base): 5.5 lb container
Part B (Curing Agent): 5.5 lb container
Part C (Aggregate): 5.5 lb container

Mixing Ratio: The three ZYCrete PMC-120 components (Parts A, B and C) are mixed as a full kit only; 5.5 lb Part A, 5.5 lb Part B and 5.5 lb Part C. The end mixture must not be reduced with solvent

Application: Using a v-notched (up to 1/8") or smooth squeegee, evenly spread the material to produce an even coat (no less than 120 sq ft) and back-roll with a 3/8" lint free roller. If multiple pours are required, pour the next batch 2" into the wet edges and repeat the same process.

Average Dry Time at 70°F (21°C): Dry times vary depending upon weather conditions. **Dry Time (70°F; 21°C):** 6 - 8 hours; **Working Time (70°F, 21°C):** 25 minutes; **Light Foot Traffic (70°F; 21°C):** 24 hours; **Vehicle Traffic (70°F; 21°C):** 24 hours; **Full Cure at 70°F (21°C):** 24 hours.

ZYCRETE PMC-120

Polymer-Modified Cement for Minor Concrete Imperfections

Technical Data (Con't):	<i>Data / results may differ due to statistical variations, mixing methods and equipment, temperature, application methods, actual site conditions and curing conditions</i>
Resistance To:	Moisture, stains, chemicals and abrasion (e.g., water, mold, mildew, salt, grease, oil spills, brake fluid, gasoline, hydraulic fluid, xylene, MEK, bases (sodium hydroxide), and acids (hydrochloric, sulphuric, acetic and nitric acids)
Reducing:	Do not reduce.
UV Stability:	Not light stable; sunlight and metal halide lighting will cause yellowing
% Solids (Wt):	High solids; 100%
VOC:	0 grams/liter
Hardness, Shore D:	80 D (ASTM D-2240)
Compressive Strength:	9000 psi (ASTM C-579)
Theoretical Coverage:	At 14 – 16 mils, minimum 120 sq ft
Tensile Strength:	1200 psi (ASTM C-307)
Flexural Strength:	2000 psi (ASTM C-580)
Adhesion to Concrete:	>400 psi (ASTM D-7234)
Impact Resistance:	>160 in/lb (ASTM D-2794)
Water Absorption:	>0.10% (ASTM C-413)
Abrasion Resistance:	70 mg loss (ASTM 4060; 1 K load, 1000 cycles, CS17 wheel)
Pot Life:	Pot Life = 15 – 20 minutes at 70°F (21°C).
Shelf Life:	12 months when Parts A, B and C are not combined, unopened and stored indoors at temperatures between 50°F (10°C) and 100°F (38°C)

ZYCRETE PMC-120

Polymer-Modified Cement for Minor Concrete Imperfections

Mixing: ZYCrete PMC-120 is a three-component system: Part A base, Part B curing agent and Part C aggregate. Shake Part A thoroughly before opening. To mix, pour the contents of Part A into a 5-gallon metal mixing pail and add Part B. Mix for 30 seconds. Gradually add the Part C aggregate and mix at high speed for 2 minutes, scraping the sides of the mixing pail into the mix to obtain an evenly blended product. Check for clumps.

Application Procedure: Application is only effective between 40°F and 90°F; do not apply above 90°F. ZYCrete PMC-120 may be used in a variety of coating systems and is typically used as a primer, midcoat or color coat.

Handling and Storage: Store in a cool, dry, well ventilated area. Keep containers tightly closed.

• KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • INDUSTRIAL GRADE • HANDLING AND INSTALLATION MUST BE PERFORMED BY ECO-CORFLEX-CERTIFIED APPLICATORS ONLY •

All information provided by Eco-CorFlex concerning its products, including but not limited to, any recommendations and advice relating to the application and use, is given in good faith based on Eco-CorFlex's current experience and knowledge of its products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Eco-CorFlex's control are such that Eco-CorFlex assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of Eco-CorFlex product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application. Eco-CorFlex reserves the right to change the properties of its products without notice.

Prior to each use of any Eco-CorFlex product, the user must read and follow the warnings and instructions on the products most current Technical Data Sheet, product label and Safety Data Sheet which are available online at www.ecocorflex.com or by calling Eco-CorFlex at 866-406-2628. Eco-CorFlex warrants this product to be free of manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within the shelf life. User determines suitability of product for intended use and assumes all risks. The buyer's sole remedy shall be limited to the purchase price or replacement of product *exclusive of labor or cost of labor*.

ECO-CORFLEX MAKES NO OTHER WARRANTY, EXPRESSED OR IMPLIED, AND ALL WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY DISCLAIMED.