

**Industrial Flooring**

## SL EPOXY II (CLEAR)

No VOC, Low Odor Industrial Clear Coat

**Description:** Two-component, low-odor, zero-solvent, zero-VOC, 100% solids, high-build self-leveling (SL) epoxy clear. SL Epoxy II is perfect for **use as a clear coat for all interior installations**. Easy-to-apply, delivers a high gloss finish, and provides extreme chemical, impact, abrasion and wear resistance.

**Areas of Usage:** Perfect for basements, kitchens, warehouses, manufacturing facilities, shop floors, clean rooms, laboratories, aircraft hangars. **Not to be used as a top coat on any exterior surface.**

<b>Features / Advantages:</b>	Self-leveling clear	High solids and solvent free
	Chemical resistance	Seamless, high-build coat
	High gloss	Impact, abrasion and wear resistant
	Zero VOCs	24-hour return to service
	Low odor	Low maintenance

**Surface Preparation:** Allow new concrete to cure for at least 30 days prior to preparation and coating. Test for moisture. Remove dust, oil, grease, curing compounds, scale and other contaminants. Prepare concrete via mechanical abrasion (grinding, diamond grinding) to achieve a surface profile equivalent to ~CSP3. Apply a proper moisture-mitigating primer coat (100%-solids MME) and/or color coat prior to application of SL Epoxy II.

**Technical Data:** *Note: Data / results may differ due to statistical variations, mixing methods and equipment, temperature, application methods, actual site conditions and curing conditions*

**Packaging:** Part A: 5 US-gallon pail (18.9 L); weight of 55 lbs  
Part B: 5 US-gallon pail (18.9 L); weight of 46 lbs

**Mixing Ratio:** Two (2) parts Part A to one (1) part Part B (i.e., 2:1 ratio); the mixture should not be reduced with solvent. *(Refer to important mixing instructions on page 3 of this TDS)*

**Application:** For **solid and partial-chip applications**, snowplow with a 14" or 18" (3/8" shed-resistant) roller or 3/16" notched rubber squeegee for horizontals and polyester brush for peripheries. Immediately back-roll material with roller (do not back-roll after mixture begins to tack up).  
For **full-chip applications**, snowplow using a 22" Kraft Squeegee Trowel and cross-hatch. Do not back-roll.

**Average Dry Time at 77°F (25°C):** Dry times vary depending upon weather conditions. **To Touch at 72°F (22°C):** 4-6 hours; **Re-coat at 72°F (22°C) (Min/Max):** 6 - 24 hours; **Light Foot Traffic at 72°F (22°C):** 12 hours; **Full Cure at 72°F (22°C):** 7 days.

## SL EPOXY II (CLEAR)

No VOC, Low Odor Industrial Clear Coat

<b>Technical Data (Con't):</b>	<i>Data / results may differ due to statistical variations, mixing methods and equipment, temperature, application methods, actual site conditions and curing conditions</i>
Resistance To:	Moisture, stains, chemicals and abrasion (e.g., water, mold, mildew, salt, grease, oil spills, brake fluid, gasoline, hydraulic fluid, xylene, bases and acids (hydrochloric, sulphuric, acetic and nitric acids))
Reducing:	Do not reduce
Finish:	High gloss
Colors:	Clear
% Solids (Vol):	High solids; 100%
% Solids (Wt):	High solids; 100%
VOC:	0 grams/liter
Curing Mechanism:	Chemical reaction between components
Theoretical Coverage:	For <b>partial chip applications</b> , apply ~6-7 mil per sq ft (0.4 gal per 100 sq ft). For <b>full-chip applications</b> (application in a single coat), apply ~8.5 mils (0.5 gal per 100 sq ft).
Flexural Strength:	12,800 psi (ASTM D790)
Hardness, Shore D:	Not available
Adhesion Testing:	500 psi (substrate failure)
Pot Life:	Pot Life = 20 - 25 minutes @ 72°F (13°C)
Shelf Life:	Twelve (12) months when Parts A and B are not combined, unopened and stored indoors at temperatures between 40°F (10°C) and 100°F (38°C) out of the sun.

## **SL EPOXY II (CLEAR)**

No VOC, Low Odor Industrial Clear Coat

**Mixing:**

Prior to mixing, heat Part A and Part B containers to a minimum 85°F to ensure proper flowability. Add 2 parts A and 1 part B in a bucket; mix immediately. Using a digital infrared thermometer, assess the temperature of the mixture. It must be min. 85°F (otherwise, allow mixture to remain in the container until the temperature is attained). *Do not reduce*. Always mix at a slow mixing speed to avoid introducing air into the mixture. If polypropylene anti-skid is to be incorporated in the mixture, add the required quantity and re-mix (do not exceed 4 ounces polypropylene anti-skid per 1 - 1 ½ gallons of the mixture).

**Application Procedure:**

Snowplow with a 14" or 18" roller (3/8" shed-resistant) or 3/16" notched rubber squeegee for horizontals and polyester brush for peripheries. Immediately back-roll. Do not back-roll after mixture begins to tack up.

**Handling and Storage:**

Store in a cool, dry, well ventilated area. Keep containers tightly closed.

- **KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN**
- **NOT FOR INTERNAL CONSUMPTION • INDUSTRIAL GRADE • HANDLING AND INSTALLATION MUST BE PERFORMED BY ECO-CORFLEX-CERTIFIED APPLICATORS ONLY •**

All information provided by Eco-CorFlex concerning its products, including but not limited to, any recommendations and advice relating to the application and use, is given in good faith based on Eco-CorFlex's current experience and knowledge of its products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Eco-CorFlex's control are such that Eco-CorFlex assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of Eco-CorFlex product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application. Eco-CorFlex reserves the right to change the properties of its products without notice.

Prior to each use of any Eco-CorFlex product, the user must read and follow the warnings and instructions on the products most current Technical Data Sheet, product label and Safety Data Sheet which are available online at [www.ecocorflex.com](http://www.ecocorflex.com) or by calling Eco-CorFlex at 866-406-2628. Eco-CorFlex warrants this product to be free of manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within the shelf life. User determines suitability of product for intended use and assumes all risks. The buyer's sole remedy shall be limited to the purchase price or replacement of product *exclusive of labor or cost of labor*.

**ECO-CORFLEX MAKES NO OTHER WARRANTY, EXPRESSED OR IMPLIED, AND ALL WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY DISCLAIMED.**