

## **POLY ENHANCE (CLEAR)**

Chemical Resistant, UV-Stable Sealer

**Description:** Two-component low-viscosity acrylic urethane coating, primarily for exterior applications. Used to prime or seal various substrates including concrete, decorative or stamped concrete, exposed aggregate, paver stone and brick.

**Areas of Usage:** Patios, walkways, driveways, handicap ramps, parking lots, well-ventilated warehouses, manufacturing facilities, storage areas, laboratories, airplane hangars, and unoccupied (new builds) washrooms, showers, garages, and basements. May be used as a sealer to clearcoat substrates where extreme chemical resistance and/or UV protection are required.

<b>Features / Advantages:</b>	Clear sealer	Color enhancement
	Excellent stain resistance	Moisture and abrasion resistant
	Excellent gloss retention	Easily re-coated
	UV stability	Rapid cure rate
	Excellent penetration & adhesion	Low VOC option available

**Surface Preparation (When Used as a Sealer):** In all cases, remove dust, laitance, grease, rust or other contaminants. Where applicable, prepare concrete via mechanical abrasion (grinding) or chemical treatment (acid washing or stripping). Preparation may involve neutralization with an alkali followed by a thorough rinse.

**Technical Data:** *Note: Data / results may differ due to statistical variations, mixing methods and equipment, temperature, application methods, actual site conditions and curing conditions*

**Packaging:** Available in 5-gallons containers (Part A and Part B) and as 1.5-gallon kits consisting of a 1-gallon Part A container and a 0.5-gallon Part B catalyst container

**Mixing Ratio:** Two parts Part A to one part Part B Activator (i.e., 2:1 ratio); the mixture may be reduced with acetone only

**Application:** The preferred method is to spray on clear Poly Enhance using an acetone-resistant pump sprayer immediately followed by backrolling (i.e. 2 applicators are required to work simultaneously). However, a polyester brush, 9", 14" or 18" roller with microfiber nap may also be used. Two coats are required.

**Average Dry Time at 77°F (25°C):** Dry times vary depending upon weather conditions. **Cure to Tack-Free:** <3 hours; **Waiting Time Between Coats:** 1 – 2 hours; **Cure to Light Foot Traffic:** 24 hours; **Full Cure:** minimum of 4 days

**Chemical & Stain Resistance:** Resistant to coffee, mustard, whiskey, urine, gasoline, motor oil, brake fluid, transmission fluid, skydrol, mineral spirits, 10% sulphuric acid, 10% hydrochloric acid, 10% acetic acid, xylene and MEK (ASTM D-1308 24-hour immersion)

**Reducing:** May be reduced with acetone only. Poly Enhance must never be reduced with any other solvent

## **POLY ENHANCE (CLEAR)**

Chemical Resistant, UV-Stable Sealer

**Technical Data (Con't):** *Data / results may differ due to statistical variations, mixing methods and equipment, temperature, application methods, actual site conditions and curing conditions*

Finish:	High gloss (60 degrees). Sheen "dies down" over time to a soft patina
Colors:	Clear
% Solids (Wt):	Average of 38%
Vehicle Type:	Modified acrylic
Viscosity:	Low viscosity
Physical Properties:	VOC Actual: 400 g/L; California Formulation: 38 g/l
Thickness:	Recommended 2 - 3 mils DFT per application (preference is for 2 or more medium applications using an approved acetone-resistant sprayer)
Hardness:	127 (Konig)
Flexibility:	Passes 1/8 inch (ASTM D-222)
Impact Resistance:	Passes 3/8 inch-pounds direct impact (ASTM D-2794)
Pot Life:	Pot life pertains to material contained in the sprayer reservoir. Pot Life = 1 hour at 77°F (25°C); gradual thickening of product will occur
Tabor Abrasion:	69 mg. Loss
Adhesion to Concrete:	Concrete fails before loss of bond (ASTM 451)
Shelf Life:	6 months at 77°F (25°C) when Parts A and B are not combined

**Mixing:** Poly Enhance is a two component system: Part A and Part B (the activator). When ready to use, mix Part A and Part B in a ratio of 2:1:1 as follows: add 2 parts Part A and 1 part Part B in a bucket and mix immediately. Mix at a slow speed to avoid introducing air into the mixture. After thoroughly mixing Parts A and B, add 1 part acetone as a reducer and re-mix thoroughly. If coating paver stone or brick, use a ratio of 2:1:2 (in lieu of 2:1:1).

**Application Procedure:** Clear Poly Enhance may be used on a variety of substrates and is used as a clearcoat system.

**Handling & Storage:** Store in a cool, dry, well ventilated area. Keep containers tightly closed.

## **POLY ENHANCE (CLEAR)**

Chemical Resistant, UV-Stable Sealer

---

**• KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • INDUSTRIAL GRADE • HANDLING AND INSTALLATION MUST BE PERFORMED BY ECO-CORFLEX-CERTIFIED APPLICATORS ONLY •**

All information provided by Eco-CorFlex concerning its products, including but not limited to, any recommendations and advice relating to the application and use, is given in good faith based on Eco-CorFlex's current experience and knowledge of its products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Eco-CorFlex's control are such that Eco-CorFlex assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of Eco-CorFlex product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application. Eco-CorFlex reserves the right to change the properties of its products without notice.

Prior to each use of any Eco-CorFlex product, the user must read and follow the warnings and instructions on the products most current Technical Data Sheet, product label and Safety Data Sheet which are available online at [www.ecocorflex.com](http://www.ecocorflex.com) or by calling Eco-CorFlex at 866-406-2628. Eco-CorFlex warrants this product to be free of manufacturing defects and warrants this product to meet the technical properties on the current Technical Data Sheet if used as directed within the shelf life. The user must determine suitability of each product for its intended use and assumes all risks. The buyer's sole remedy shall be limited to the purchase price or replacement of the product *exclusive of labor or cost of labor*.

**ECO-CORFLEX MAKES NO OTHER WARRANTY, EXPRESSED OR IMPLIED, AND ALL WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY DISCLAIMED.**